

# FL 200 filter sheet

Part No.: 1131



## Application area

FL 200 is part of our FL filter sheet range. The FL 200 filter layer is primarily used to serve filtration purposes in green roof build-up where it is rolled out over the drainage layer. An overlapping of at least 100 mm is required between the adjacent filter sheets. Openings must be cut in the filter sheet above the roof outlets.

## Benefits

- ☑ excellent water permeability and ventilation properties
- ☑ low clogging index
- ☑ withstands point stresses
- ☑ resistant to acids and alkalis
- ☑ made of virgin polypropylene, includes a 25-year warranty to perform its function
- ☑ complies with FLL - Guidelines for the Planning, Execution and Upkeep of Green-roof sites 8.2 / 2002

## Technical data

Material	Polypropylene
Thermal treatment	Non-treated
CE marking	Affixed
Weight per unit area (EN ISO 9864)	200 g/m <sup>2</sup>
Tensile strength (EN ISO 10319)	
warp (MD)	15 kN/m
weft (CMD)	15 kN/m
Elongation at break (EN ISO 10319)	
warp (MD)	60 %
weft (CMD)	60 %
CBR puncture (EN ISO 12236)	2.9 kN
Pore size, O <sub>90</sub> (EN ISO 12956)	0.10 mm
Water permeability normal to the plane	
V <sub>IH50</sub>	80 mm/s
q	80 l/m <sup>2</sup> ·s
(EN ISO 11058)	
Width / length / area of roll	2 m / 100 m / 200 m <sup>2</sup>
Weight / diameter of roll	40 kg / 55 cm
Colour	black



## Specification suggestion

ArchiGreen® FL 200 is CE-certified, needled felt made of thermally non-treated, non-rotting virgin polypropylene fibres. It serves as a filter layer in an intensive green roof build-up. Surface weight: 200 g/m<sup>2</sup>; thickness: 2.5 mm; CBR test EN ISO 12236: 2.9 kN; tensile strength EN ISO 10319: 15 kN/m, elongation at break MD/CMD: 60/60%; pore size EN ISO 12956: d<sub>90</sub> = 0.1 mm; water permeability EN ISO 11058: 80 mm/s, q: 80 l/m<sup>2</sup>·s; laid with an overlap of 100 mm. Complies with FLL guidelines 8.2 / 2002.

## Installation example

